



“LITERATURE REVIEW FOR SHEAR STRENGTH OF HIGH STRENGTH CONCRETE SLENDER BEAMS WITH AND WITHOUT TRANSVERSE REINFORCEMENT”

Vinod yadav, Civil Engineering Department, Technocrat Institute of Technology-Computer Science and Engineering, Bhopal Pin Code, 462022, Madhya Pradesh, India.

Dr. Md Imran Khan Civil Engineering Department, Technocrat Institute of Technology- Bhopal Pin Code, 462022, Madhya Pradesh, India.

Prof Aajid Khan. Civil Engineering Department, Technocrat Institute of Technology- Bhopal Pin Code, 462022, Madhya Pradesh, India.

Abstract:

The shear failure of HSC beams is a very complex fracture phenomenon and associated with brittle failure and it becomes very difficult to predict shear capacity by mathematical approach or empirical formulas and the various international codes are very conservative for prediction of shear strength of HSC beams so an experimental investigation has been carried out to predict the shear capacity of HSC beams and compare with the code provision.

A total 32 number of HSC slender beams of M 70 grade were casted and tested for the study of shear capacity and brittle shear failure. The shear and flexural capacity of the beams were theoretically calculated, the shear and flexural reinforcement were so selected to ensure shear failure of all the beams. The cross-sectional dimension of all the beams were such that the width was constant, the depth of the beam was varied, the other parameters like % of longitudinal reinforcement, shear reinforcement, shear span to depth ratio, length of the beam were varied. The beams were tested under four-point loading (2 active and 2 passive). The load-deflection curves were plotted and the theoretical and experimental loads of the beams i.e. shear strength of the beam was compared and tabulated and suitable conclusions were drawn.

Keywords: Shear strength, shear failure, compressive strength of concrete, transverse reinforcement, longitudinal reinforcement, shear span to depth ratio.

I- INTRODUCTION:

Amount of stirrup has a direct relation on the behavior of reinforced concrete members of general structure, since the structures are possible to fail in brittle manner without any warning sign if the shear stress rides over the shear carrying capacity.

Great example of shear failure is the collapse of super-structures during Great-Hanshin Earthquake, in 1995. With respect to that evident, many of viaduct's structures constructed as a rigid-framed were destructed as shown in Figure 1-1. According to the mentioned structure, the amount of stirrup was lightly used. Therefore, the following question has been asked by many researchers for such a longtime that did the estimation of shear strength of those was miscalculated?

One of possible and discovered reason is the size effect of the structure members, which was introduced by Okamura [2]. With respect to this reason, the formula derived from the specimen in experiments, which are very tiny compare to the real structure, did not include some important factor. It can be illustrated that strength of small specimens in experiments are affected in crack propagation by the reinforcing bar, so called bond effect, which increased the fracture energy of concrete. Nevertheless, in actual, the effect of bond from the reinforcement is very tiny since the members cross-section is so large that crack propagation is not able to confine by bond effect of reinforcement. It used to clarify and accept this problem, size effect, by many researchers and the consideration in its was added as size effect term in the shear strength design formula.

Another possible problem but it does not clarify yet is the shear carrying capacity's design concept since the concept is used as the strength of concrete at either failure or shear crack load and sum up with shear resistance of web reinforcement. Why the shear strength design concept seems to be not enough, it is possible that a small amount of web reinforcement cannot maintain the shear



strength resist by concrete to be the same up to yielding point of stirrup itself. The remaining and possible reason is going to study [4].

1.2 Current Use of Stirrup

As mentioned, the important factors drive shear failure in super-structure during Kobe's earthquake was explored. One factor originally based on the past design code since it used to overestimate in size-effect.

A related consideration is because Japan Society of Civil Engineering's design guide at the constructing period used allowable stress design concept, and it had required a suddenly increasing of stirrup if the allowable shear strength of concrete did not enough. Consequently, escaping from suddenly increasing of stirrup, enlarge section of member to increase the allowable shear stress in concrete was commonly done. In summary, large section and small amount of stirrup are the consequence of designing that finally destructed by the earthquake.

The shear strength of reinforced concrete beams has been extensively studied over the last 40 years. for the case of slender beams with shear reinforcement under two point loading large number of experimental and analytical works have been carried out. More over in shear reinforcement to control the inclined cracking in beams have been determined.

Despite the great research efforts, however, there is still not a simple, albeit analytically derived formula to predict and with accuracy the shear strength of slender beams. In addition, many of the factors that influence the determination of the required minimum amount of shear reinforcement are not yet known [3].

Unlike flexural failures, reinforced concrete shear failures are relatively brittle and particularly for members without stirrups can occur without warning because of this, the prime objective of shear design is to identify where shear reinforcement is required to prevent such a failure and then in a less-critical decision how much is required. Shear reinforcement, usually called stirrups links together the flexure tension and flexure compression sides of a member and ensures that the two sides act as a unit.

Shear failures involve the breakdown of this linkage and for members without stirrups, typically involves the opening of major diagonal crack. With advent of higher concrete compressive strengths and the corresponding increase in concrete tensile strengths there is concern that traditional amounts of minimum shear reinforcement may not be sufficient in high strength concrete beams. Minimum shear reinforcement must prevent sudden shear failure on the formation of first diagonal tension cracks at service loads levels.

To prevent brittle failures adequate reserve strength must be provided by the shear reinforcement after diagonal cracking of reinforced concrete beams. To control crack widths at service loads levels not only a minimum amount of shear reinforcement be provided but the maximum stirrup spacing must also be limited. Due to the higher tensile strength of high –strength concrete a higher cracking shear is expected and hence would require a larger amount of minimum shear reinforcement [4].

1.3 Shear Study:

1)The mechanism of shear resistance in RCC beams without web reinforcement

In a reinforced concrete members, flexure and shear combine to create a biaxial state of stress. Cracks form when the principle stresses exceed the tensile strength of the concrete. In a region of large bending moments these stresses are greatest at the extreme fiber of the member and are responsible for the initiation of flexural cracks perpendicular to the axis of the member.

In the region of high shear force significant principle stresses also referred to as diagonal tension may be generated at a approximately 45 degrees to the axis of the member. These may result in inclined cracks. With few exceptions these inclined cracks are extensions of flexural cracks. Only in rather special cases as in webs of flanged beams, are diagonal tension cracks initiated in the vicinity of the neutral axis. The principle stress concept is of little value in the assessment of subsequent behavior unless complex distribution of stresses in the concrete after cracking is



considered. Either a reinforced concrete flexural member collapse immediately after the formation of diagonal cracks or an entirely new shear carrying mechanism develops which is capable of sustaining further load in a cracked beam.

The diagonal cracking load originating from flexure and shear is usually much smaller than would be expected from principle stress analysis and the tensile strength of concrete.

This condition is largely due to the presence of shrinkage stresses, the redistribution of shear stresses between flexural cracks and the local weakening of a cross section by transverse reinforcement which causes a regular pattern of discontinuities along a beam.

In the early stages of reinforced concrete design diagonal cracking was considered to be undesirable. However, it is now recognized that diagonal cracking under service load conditions is acceptable, provided crack widths remain within the same limits accepted for flexure.

Shear strength in steel reinforced concrete beams has been the subject of many controversies and debates since the beginning of 20th century. The shear strength of reinforced concrete beams has been extensively studied over the last five decades [6].

A large number of experimental and analytical works have been carried out for the case of slender beams (having a shear span to depth ratio $a/d > 2.5$) with and without shear reinforcement under two-point loading.

Transversely loaded reinforced concrete beams may fail in shear before attaining their full flexural strengths if they are not adequately designed for shear. Unlike flexural failures, shear failures are very sudden and unexpected, and sometimes violent and catastrophic. A thorough knowledge of the different modes of shear failures and the mechanisms involved is necessary to prevent them.

Existing codes and specifications of different countries for reinforced concrete design with regard to shear differ considerably in important aspects. This only reflects the fact that we know very little about the behavior and strength of reinforced concrete subjected to shearing force in spite of the considerable number of tests and theoretical investigations made during more than half a century.

Despite the great research efforts, however, there is still not a simple, albeit analytically derived formula to predict quickly and accurately the shear strength of slender beams. In addition, many of the factors that influence the determination of the required minimum amount of shear reinforcement are not yet known [15].

II- LITERATURE REVIEW:

THEODOR KRAUTHAMMER (JAN/FEB- 1992),[1] In this paper the requirement for minimum shear reinforcement in RCC beams is evaluated based on the treatment of interface shear transfer across a crack. A key parameter for this derivation is required magnitude of contact normal stress on such interface which controls the frictional resistance. The experimental data were employed to define the required value of the normal contact stress and its incorporation into the proposed approach resulted in a modified definition for shear reinforcement. This approach enabled the derivation of two useful tools for the design of interface shear resistance and minimum shear reinforcement in RCC beams. The research significance is that it provides a rational approach to determine minimum shear reinforcement requirement to ensure adequate safety. The requirement for minimum shear reinforcement in reinforced concrete beams

MICHAEL P. COLLINS, EVAN C. BENTZ AND EDWARD G. SHERWOOD(2008),[2]

M60 grade rein This paper concludes that using the current ACI shear provisions to decide where shear reinforcement is required can be conservative for members with larger effective depths or higher stresses in the longitudinal reinforcement. Improvement to the ACI code is proposed to mitigate these weaknesses. The paper also demonstrates that the AASHTO-LRFD and Canadian CSA sectional and strut and tie provision a more uniform level of safety for all member types. Study behavior of high strength concrete leads to significant changes in codal provisions in practice around the world, it shows that HSC needs different philosophy of design and approach, computed the



concrete compressive strength using standard specimens, taking different load and resistance factors to obtain specified characteristic strength, modulus of elasticity, tensile strength of concrete, minimum reinforcement for flexure and even seismic design.

YOUNG-SOO, WILLIAM D. COOK AND DENIS MITCHELL (1996), [3]

They presented on the evaluation of minimum shear reinforcement requirement in normal, medium and high strength reinforced concrete beams. 12 shear tests were conducted on full scale beam specimens having concrete compressive strength of 36, 67, 87 Mpa. Different amounts of minimum shear reinforcement were investigated including traditional amounts required by older codes. The performance of the different amounts of shear reinforcement are discussed in terms of shear capacity, ductility and crack control at service loads levels. An assessment of the 1989 ACI and 1991 CSA provision for minimum shear reinforcement. The evaluation of minimum shear reinforcement requirements in normal, medium, and high-strength reinforced concrete beams. Twelve shear tests were conducted on full-scale beam specimens having concrete compressive strengths of 36, 67 and 87 Mpa. Different amounts of minimum shear reinforcement were investigated, including the traditional amounts required by older codes and the amount required by 1989 ACI code. The performances of the different amounts of shear reinforcement are discussed in terms of shear capacity, ductility and crack control at service load levels. An assessment of the 1989 ACI and 1994 CSA provisions for minimum shear reinforcement is also presented based on crack control, ductility high strength concrete, minimum shear reinforcement, shear strength, splitting cracks stirrups. Based on beam support, shear strength, shear reinforcement and splitting cracks.

SONGKRAM PIYAMAHANT (2002), [4]

According to the advance concerning, the shear carrying capacity of reinforced concrete beam in concrete part after cracking should not be regard to be the same as just crack, but it should be changed. However, in that experiment, the amount of stirrup used as much larger than the minimum requirement. Nevertheless, at least, the behaviors of it after cracking like either load resistance or crack opening and crack sliding, which control the load-deformation of itself, it mainly depends on the amount of stirrup.

In summary, the shear carrying capacity of reinforced concrete beam with web reinforcement does not simply sum up that of concrete and stirrup together as $V_c + V_s$, but it has to concern with the interaction between them, which actually depend on amount of web reinforcement.

Y-H. BAE, J-H LEE AND Y-S YOON (2006), [5]

The ultimate high-strength equation considering size effects and arch action is presented for computing the shear strength in high-strength concrete beams without stirrups, 3 basic equations namely those for the size reduction factor and arch action factor are derived from the crack band model of fracture mechanics, analysis of previous shear equations for longitudinal reinforcement ratio and concrete strut described as a linear function in deep beams. constants of basic equations were determined using statistical analysis of previous shear testing data. while the proposed shear equation is simpler than other shear equations i.e ACI 318, CSA 34 and it gives economical predictions of shear strength and reasonable safety margin.

The conclusions drawn are that shear strength of HSC beams as a/d ratio decreased owing to higher arch action, effect of aggregate type has negligible effect on shear strength. From comparison, it was found that the IS 456 (2000) code gives most conservative results of HPC beams while, the ACI 318 (2005) and Eurocode 2 (2004) codes are comparatively satisfactory.

IMRAN A. BUKHARI* AND SAEED AHMAD (2007), [7]

In this paper, a comparative analysis on shear behaviour of high-strength concrete beams using various international design approaches like ACI, Canadian, AASHTO, European Code and the method proposed by Zararis is presented. Twenty-seven reinforced concrete beams without web reinforcement were tested under three-point loading. In addition, 95 other similar beams having similar cross-sectional dimensions, concrete strength, and loading conditions are analysed. The shear span-to-depth ratio ranged from 1 to 6 and longitudinal reinforcement ratio from 0.35% to 1.94%.



Based on the analysis of total of 122 similar beams, it is observed that shear strength and failure mode depend upon shear span and longitudinal reinforcement ratio. For values of a/d ratio less than 2.5, the experimental shear strength was found greater than that predicted as per different shear design approaches; however for slender beams having a/d ranging from 2.5 to 6, the predicted shear capacity was found greater. It was noted that ACI 318-02[1] predicts shear strength more accurately for values of tensile steel ratio greater than 1%, whereas design approach proposed by Zararis is more appropriate to be used where tensile steel ratio is less than 1%.

GURAY ARSLAN (2008), [8]

This study presents alternative cracking shear strength equations for slender reinforced concrete (RC) beams without stirrups. More than 80 data have been obtained from existing sources of RC beam shear test results covering a wide range of beam properties and test methods. The proposed cracking shear strength equations are applied to existing test data for normal strength concrete (NSC) and high-strength concrete (HSC) slender beams and the results are compared with those predicted by the ACI 318 equations. It can be also noted that the test results are in better agreement with proposed cracking shear strengths. However, because the test data for high-strength concrete members are very limited, further research is required to verify these equations.

The cracking shear strength equation for slender reinforced concrete high strength beams without stirrups are developed based on test results and experimental investigations of wide range beams based on their properties and test methods, the equations are applied both for NSC and HSC beams, it is noted that test results are in better agreement with proposed cracking shear strength for HSC based on compressive strength, cracking shear strength, shear span at depth, dowel action and diagonal tension and the equation obtained are compared with different national codes which shows significant scatter between the experimental values and codal provisions.

S.M. GUPTA, V.K. SEHGAL, S.K. KAUSHIK (2009), [18]

This paper presents the results of an experimental investigation carried out to evaluate the shrinkage of High Strength Concrete. High Strength Concrete is made by partially replacement of cement by fly ash and silica fume. The shrinkage of High Strength Concrete has been studied using the different types of coarse and fine aggregates i.e. Sandstone and Granite of 12.5 mm size and Yamuna and Badarpur Sand. The Mix proportion of concrete is 1:0.8:2.2 with water cement ratio as 0.30. Super plasticizer dose @ of 2% by weight of cement is added to achieve the required degree of workability in terms of compaction factor. From the test results of the above investigation, it can be concluded that the shrinkage strain of High Strength Concrete increases with age. The shrinkage strain of concrete with replacement of cement by 10% of Fly ash and Silica fume respectively at various ages are more (6 to 10%) than the shrinkage strain of concrete without Fly ash and Silica fume. The shrinkage strain of concrete with Badarpur sand as Fine aggregate at 90 days is slightly less (10%) than that of concrete with Yamuna Sand. Further, the shrinkage strain of concrete with Granite as Coarse aggregate at 90 days is slightly less (6 to 7%) than that of concrete with Sand stone as aggregate of same size. The shrinkage strain of High Strength Concrete is also compared with that of normal strength concrete. Test results show that the shrinkage strain of high strength concrete is less than that of normal strength concrete.

M Hamrat , B Boulekbache, and S Amziane et al (2016), [26]

This paper presents the results of an experimental investigation dealing with the effects of transverse reinforcement on the crack patterns, the ultimate carrying capacity and the ductility of beams made of high strength concrete and normal strength concrete for comparison purposes. The test results are analyzed and compared with the shear provisions in the four major universal codes (ACI-318; BS-8110; Eurocode 2; BAEI 99). Twenty-six reinforced concrete beams with and without transverse reinforcement were constructed using different shear-span to depth ratios ($a/d = 1.5, 2.0$ and 3.0) and different compressive strengths of concrete (44 MPa, 65 MPa and 86 MPa).

The test results indicate that the presence of transverse reinforcement had controlled efficiently the crack width by enhancing the aggregate interlocking on the crack surface, increased moderately

the shear strengths of the beams by factors ranging from 1.14 to 1.86, and increased appreciably the ductility of beams at the ultimate state. It should be noted, however, that the beams failed at shear strength contributions of transverse reinforcement (V_s) considerably lower than the values predicted by the models used in the four major universal codes. This translates that the existing universal design codes may not be rationally safe against shear design of high strength concrete beams containing transverse reinforcement.

Subhan Ahmad , Pradeep Bhargava , Ajay Chourasia , Minkwan Ju et al (2021), [27]

Forty-eight reinforced concrete (RC) beams without transverse reinforcement were tested at ambient and after exposure to high temperatures. Beams were heated to high steady-state temperatures of 350 °C, 550 °C, and 750 °C in a programmable closed electric furnace and loaded to failure after cooling down. In addition to exposure temperature, tension reinforcement percentage (ρ) and shear-span-to-depth ratio (a/d) were kept as the variables. In the beams tested at ambient and after the elevated temperature of 350 °C, beam action was dominant, and diagonal tension failure was the observed mode of failure. When beams were exposed to 550 °C and 750 °C, beam action almost vanished, and the beams failed due to the failure of a compression strut joining the loading point and the support. After exposure to high temperatures, shear strength loss observed in beams with a lower tension reinforcement ratio was found to be more significant. Whereas, change in a/d ratio had an insignificant influence on the shear strength loss of the beams. An increase in temperature resulted in the decrease of the beams stiffness and increased the deflection corresponding to the ultimate load. An empirical model was also developed from the data of the present study for the prediction of shear strength of RC slender beams exposed to high temperatures.

III- CONCLUSION:

The following conclusions were made from the experimental investigation

1. Mix proportion for HSC M70 was obtained using chemical admixture and without using mineral admixture and the average 28-day strength was found to be 80 Mpa.
2. As the percentage of longitudinal reinforcement increased from 1.8% to 3.2%, the shear strength of HSC beams also increased (dowel shear contribution increased), it was significant for small spacing of shear steel (150,225mm) , but this was not significant for beams without web reinforcement and large spacing of stirrups (300mm) Failure becomes more sudden and explosive as the longitudinal steel ratio increases from 1.8% to 3.2%.
3. As the depth of the HSC beams increased, the deflection decreased and the load carrying capacity (shear capacity) increased but load carrying capacity was insignificant for beams without shear reinforcement.

IV-REFERENCES:

- [1] ASTM – C 618-93: American Standard Specification for Coal Fly Ash & Raw or Calcined Natural Pozzolan for use in Concrete. Theodor krauthammer, “Minimum shear reinforcement based on interface shear transfer “, ACI structural journal jan-feb, 1992 pp 99-105
- [2] Michael p. Collins and daniel kuchma, “How safe are our large lightly reinforced concrete beams, slabs and footings?” ACI Structural journal july-august 1999, pp 482-290
- [3] Young –soo yoon, william d. Cook and denis mitchell “Minimum shear reinforcement in normal, medium and high strength concrete beams,” ACI Structural journal sept-oct 1996, pp 576-584.
- [4] Songkram piyamahant and hiroshi shima, “Shear behavior of reinforced concrete beams with a small amount of web reinforcement,” ME thesis, Kochi university of technology Kochi, Japan, Jan 2002, pp224-234
- [5] Jung-yoon lee and uk-yeon kim, “Effect of longitudinal tensile reinforcement ratio and shear span- depth ratio on minimum shear reinforcement in beams, “ACI Structural journal march-April 2008, pp 134-144.



- [6] Jin-keun kim and yon-dong park “Prediction of Shear Strength of Reinforced Concrete Beams without Web Reinforcement” ’ACI Materials Journal / May-June 1996, PP 134-147.
- [7] Imran a. Bukhari and saeed ahmad “Evaluation of shear strength of high-strength concrete beams without stirrups” ’ACI Structural journal march-July 2003, pp 154-164.
- [8] Guray arslan “Cracking shear strength of RC slender beams without stirrups “, Journal of civil engg and management, 14 July 2008, pp 177-182.
- [9] Dileep kumar “Shear strength of RCC beams without web reinforcement,”. National conference on recent development in materials and structures (redemat-2004). NIT CALICUT. Dec 2004, pp 427-436.
- [10] Virendra k. I and verma v.k,” High strength concrete application in pre-stressed concrete” ACSGE BITS Pilani, India, Oct 25-27-2009, pp165-170.
- [11] Jignesh patel I and himat solanki 2,” An analytical investigation on shear strength of high-performance concrete beams with web reinforcement” IACSGE BITS Pilani, India, Oct 25-27-2009, pp101-109
- [12] American concrete institute. ACI concrete mix design, ACI 211, revision 613-54.
- [13] AASHTO,’ code for minimum shear reinforcement ‘
- [14] ACI committee 318, “Building code requirements for structural concrete (ACI 318-05) and commentary (318-05)”’, American concrete institutes, Farmington hills, MI,2005, PP430.
- [15] “R. Park and t. Paulay” Reinforced concrete structures.
- [16] P. Rama mohan rao “Shear study on HPC beams with and without shear reinforcement”, Indian concrete journal march 2004, pp 577-583.
- [17] Yehia anis daou and hassan ghanem “Experimental study on shear strength of HSC beams with minimum shear reinforcement”, ACI Materials Journal, may1999, pp711-721.
- [18] S.m gupta, v.k sehgal, s.k kaushik “Study on properties of HSC concrete”, ACI Materials Journal Dec 2003, pp 305-315.
- [19] R.s londhe “A new shear capacity expression for transfer beams in high rise buildings”, Indian concrete journal, April 2010, pp 32-38.
- [20] M. Khuntia and b. Stojadinovic “Shear strength of RC Beams without Transverse reinforcement”, ACI structural Journals, May 1998, pp 228-236.
- [21] N. Subramanian, “Shear strength of HSRC Beams”, (codal provision review), Indian concrete Journals, march 2003, pp 114-122.
- [22] Prodromos d zararis,” shear strength & min shear reinforcement”, ACI structural journals, June 2003, pp355-455
- [23] Raghu s pendyala and priyan mendis, “shear contribution of high strength concrete”, Journals of Structural engineer ,2003, pp765-874
- [24] A. Shah & s. Ahmed,” An Experimental investigation on shear strength of HSC beams”, ASIAN Journals of civil engineering, 2007, pp205-215
- [25] IS 456:2000,’Indian standards for Plain and Reinforced concrete’.
- [26] M hamrat, b boulekbache, and s amziane “Effects of the Transverse Reinforcement on the Shear Behaviour of High Strength Concrete Beams” advance in structural engineering,2016 Vol 15, issue 8, pp 1291 – 1306.
- [27] Subhan ahmad, pradeep bhargava, ajay chourasia, minkwan ju “Residual shear strength of reinforced concrete slender beams without transverse reinforcement after elevated temperatures” Engineering Structures Volume 237,15 June 2021, 112163.